

POLYMERS FOR CONTROL OF ORIENTATION
AND STABILITY OF LIQUID CRYSTALS

CROSS-REFERENCE TO RELATED APPLICATION

This application is based on U.S. Application No. 60/194,990, filed April 5, 2000, the disclosure of which is incorporated by reference.

STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH OR
DEVELOPMENT

The U.S. Government has certain rights in this invention pursuant to grant No. F49620-97-1-0014, awarded by the Air Force Office of Strategic Research, Liquid Crystals M.U.R.I.

FIELD OF THE INVENTION

This invention relates generally to alignment materials for use in liquid-crystal electrooptic devices. More specifically, this invention relates to polymeric alignment materials that reduce or eliminate the need for separate polymeric alignment layers and provide improved mechanical stabilization to liquid crystals.

BACKGROUND OF THE INVENTION

Liquid crystal electrooptic devices such as flat panel displays rely on active alignment, or control, of the orientation of the liquid crystal molecules when no field is applied. A parameter of a liquid crystal structure, such as director orientation or smectic layer structure, may be said to be actively aligned if alignment layers induce a preferred configuration on the parameter and if when the preferred configuration is perturbed, the alignment layers exert a restoring force or torque.

There are a number of different conventional methods for controlling the orientation of the liquid crystals in the absence of a field. For example, in a twisted nematic display, the liquid crystal orientation is anchored at the surfaces on each side of the device and aligned parallel to the surfaces using rubbed polymer layers where the rubbing directions are mutually orthogonal to produce a twisted liquid crystal configuration. There are a number of difficulties associated with this approach, mainly associated with the rubbing procedure that is needed to induce the orientation in the alignment layers.

1

More problematic are smectic liquid crystal displays, such as, for example, ferroelectric liquid crystals (FLCs), used for bi-stable displays or newer analog “thresholdless FLC” devices. For FLC display panels and other smectic LCDs, the structure of the smectic layers as well as the orientation of the director is an important parameter. For existing smectic LCDs, the smectic layers of the FLC must be aligned in a “bookshelf arrangement,” and this orientation of the FLC is produced using polymer alignment layers with special thermal histories.

5

10

In addition to the same problems caused by rubbing that occur in nematic displays, a major deficiency in this means of controlling the oriented state is that they are very susceptible to mechanical disruption and alignment generally does not recover after having been perturbed by mechanical stress. However, for LCDs containing the more ordered smectic liquid crystal materials, the smectic layer structure is only passively aligned by cooling through the nematic to smectic phase transition, i.e., there is no uniquely specified periodicity in the interaction between the alignment layer and adjacent liquid crystal molecules defining the alignment which the smectic layers should adopt. Thus, if this alignment is disturbed in the smectic phase, there is no force acting to restore the original alignment. Accordingly, a small mechanical shock can disrupt the orientation state, causing orientational defects to form, which cannot be removed by any existing technology. So while smectic LCDs and, in particular, ferroelectric LCDs are strong contenders for use in high definition television (HDTV) displays, memory displays, and computer work stations, their poor resistance to mechanical shock currently limits commercial FLC devices to small sizes, typically less than a few centimeters on a side. There are known ways of reducing this problem, such as, for example, through the use of damped mountings and adhesive spacer techniques for fabrication of FLC panels. However, these techniques are not effective against all possible types of mechanical damage, such as a sudden impact or continuous pressure.

15

20

25

30

35

Several patents attempt to address the problems associated with the stability of conventional liquid crystal displays via various conventional mechanical alignment layer means. For example, JP 52 411 discloses an arrangement in which dichromatic molecules are bonded to an alignment layer. Liquid crystal molecules then align on the layer of dichromatic molecules. However, this method still has the problem of a weak alignment layer-liquid crystal layer interface. Meanwhile, EP 307 959, EP 604 921 and EP 451 820 all disclose various techniques for obtaining

1 particular structures within ferroelectric liquid crystal layers which are intended
to provide improved mechanical stability. However, the structures disclosed in the
specifications are incompatible with high speed, high contrast addressing schemes
5 and are therefore of very limited application. EP 635 749 discloses an adhesive
spacer technique for the fabrication of FLC display panels so as to provide more
resistance to mechanical damage. However, as described hereinbefore, techniques
of this type are not effective against all possible types of mechanical damage. Also,
EP 467 456 discloses the use of a liquid crystal gel layer as an alignment layer.
10 However, this type of alignment layer is used merely to control the pre-tilt angle of
the liquid crystal material in the cell and does not improve the mechanical stability.

A second method for aligning liquid crystals uses a phase-separated polymer
to control alignment and provide mechanical stability, rather than an alignment
layer. There are two general techniques, polymer-dispersed liquid crystals and
polymer-stabilized liquid crystals. These systems function similar to alignment
15 layers, in that the interactions between the liquid crystal molecules and the
polymer occur only at the interface between the solid polymer and the liquid crystal.
Typically, the polymer is synthesized in situ by photochemistry or thermally
triggered crosslinking of monomer (or macromer) dissolved into the liquid crystal.
20 As the molecular weight of the polymer grows, the system phase-separates into
polymer rich, solid and liquid crystal rich, nematic or smectic phases. The nature
of the liquid crystal orientation at the resulting liquid crystal polymer interfaces is
typically controlled by the structure of the polymer or surface-active agents that are
incorporated in the system. In some cases, the orientation direction is influenced
25 using an applied electric or magnetic field during polymerization so that the
resulting polymer provides a lasting memory of the orientation state. In this
technique the alignment polymer is made anisotropic by applying a flow or an
electric field, then after the desired orientation of the solvated monomer or
prepolymer is generated, the polymer is transformed so that it provides a lasting
30 memory of the orientation state, e.g., by photochemically or thermally-triggered
cross-linking. These techniques do improve the mechanical stability of the liquid
crystals.

For example, GB 2 274 652 discloses an arrangement in which a conventional
low molar mass ferroelectric liquid crystal mixture is doped with a polymeric
35 additive. However, while this arrangement is intended to improve mechanical

1 stability, of ferroelectric liquid crystals it results in reduced switching speed for the electrooptic device.

5 Similarly, EP 586 014 discloses arrangements of a polymer network created by photoinitiated polymerization of an aligned liquid crystal containing monomer. However, while this arrangement does improve mechanical stability, it results in reduced switching speed for the electrooptic device.

10 Finally, S. H. Jin et al, "Alignment of Ferroelectric Liquid-crystal Molecules by Liquid-Crystalline Polymer," SID 95 Digest, (1995) 536-539 discloses the use of a main chain thermotropic liquid crystal polymer as an alignment layer for an FLC cell. However, the liquid crystal alignment is obtained by conventional mechanical rubbing of this layer, the liquid crystal polymer being in its glassy phase at room temperature.

15 Accordingly, a need exists for an improved material for use in aligning liquid crystal electrooptic devices which reduces or eliminates the need for a separate alignment layer and which provides greater mechanical stabilization to a wide range of fast switching liquid crystal displays.

20 SUMMARY OF THE INVENTION

25 The present invention is directed to an electro-optically active polymer gel material comprising an alignment polymer adapted to be homogeneously dispersed throughout a liquid crystal to control the alignment of the liquid crystal molecules and confer mechanical stability. This invention utilizes a homogenous gel in which the polymer strands of the gel are provided in low concentration such that they are well solvated by the small molecule liquid crystal. A desired orientation is then locked into the gel by physical or chemical cross-linking of the polymer chains. The orientation of the polymers is then utilized to direct the orientation field in the liquid crystal in the "field off" state of a liquid crystal display. In this invention the strands of the polymer also provide a memory of the mesostructural arrangement of the liquid crystal and act to suppress the formation of large scale deviations, such as, for example, fan-type defects in an FLC when subjected to a mechanical shock.

30 In one embodiment, the invention is directed to an electro-optically active, homogeneously dispersed polymer gel layer of liquid crystalline material comprising a permanently oriented anisotropic network of polymerized material containing molecules of at least one sparsely cross-linked homogeneously dispersed polymer

35

1 solvated by molecules of at least one liquid crystalline material or mesogen, wherein
the polymer is provided in low enough concentrations such that the switching
response of the liquid crystal polymer gel is acceptably fast for electrooptic
5 operations. In one particular embodiment the polymer is adapted to mechanically
stabilize the gel. Any suitable polymer and liquid crystal mixture can be utilized
such that the polymer is fully solvated by the liquid crystal molecules, such as, for
example, a side-chain or main-chain polymer block or telechelic polymer having a
liquid crystal mesogen. Any suitable method of forming the electro-optically active
10 polymer gel layer may be utilized, such as, for example, by self-assembly of a main-
chain or side-chain block copolymer, by photopolymerization of a soluble macromer,
or by a mixture of the two.

Although any suitably dilute concentration of polymer may be utilized such
that the switching speed of the liquid crystal is not significantly reduced (for
15 example, where the switching time more than doubles over the switching time of
the pure liquid crystal molecules) and such that the polymer molecules are capable
of sparsely cross-linking to form the polymer network, in one preferred embodiment
the electro-optically active layer comprises less than 5% of the gel layer by mass and
more preferably equal to or less than 2% of the gel layer by mass.

20 Likewise, although any high molecular weight polymer may be utilized such
that the polymer is capable of sparsely cross-linking even at dilute concentrations,
in a preferred embodiment the polymer has a molecular weight of at least 100,000
g/mol, more preferably at least 500,000 g/mol, and even more preferably at least 1
million g/mol.

25 In another embodiment, the homogeneously dispersed polymer component of
the electro-optically active polymer gel is selected such that the polymer molecules
dictate the alignment of the liquid crystal molecules in the absence of an electric
field. In this embodiment any alignment geometry suitable for the desired liquid
crystal material or electrooptic device may be induced in the gel, such as, for
30 example, uniaxial, twisted, supertwisted, tilted, or bookshelf.

In yet another embodiment, the liquid crystal molecules are selected from the
group of fluorinated or cyanobiphenyl (CB) based liquid crystal molecules.

35 In still another embodiment, the network of liquid crystal molecules
comprises a plurality of self-assembly block copolymers each comprising at least one
endblock and at least one midblock, wherein the endblock either physically or

1 chemically cross-links with at least one other endblock and wherein the midblock
is soluble in the liquid crystal molecules. In such an embodiment the endblock may
be insoluble in the liquid crystal molecules thereby physically aggregating to form
5 the polymer network. In such an embodiment the midblock may further comprise
a plurality of liquid crystal side-chains, wherein the liquid crystal side-chains confer
solubility to the block copolymer in the liquid crystal molecules, or alternatively the
midblock may be a main-chain polymer comprising a plurality of liquid crystal
mesogens, and wherein the main-chain confers solubility to the block copolymer in
10 the liquid crystal molecules, or in yet another alternative the midblock may
comprise a mixed side-chain/main-chain polymer, where at least one of the main-
chain or the side-chain confers solubility to the block copolymer in the liquid crystal
molecules.

15 In such an embodiment the cross-linking may occur at any point on the
polymer chain. For example, the polymer molecules may be cross-linked only at the
ends or the midblock may further comprise at least one linking block, wherein the
linking block is either physically or chemically cross-links with either the linking
block or endblock of another polymer.

20 In still yet another such embodiment the endblock may be made crosslinkable
with other endblocks by application of either a photo or thermal initiating energy.
In such an embodiment the photo initiating energy may be any suitable energy,
such as, for example, UV-light, X-ray, gamma-ray, and radiation with high-energy
electrons or ions.

25 In still yet another embodiment, the network of liquid crystal molecules
comprises a plurality of self-assembly telechelic polymers each comprising at least
one crosslinking functional group, where the crosslinking functional group either
physically or chemically cross-links with at least one other crosslinking functional
group and wherein the telechelic polymer is soluble in the liquid crystal molecules.
In such an embodiment, the crosslinking functional group may be insoluble in the
30 liquid crystal molecules. Also in such an embodiment the telechelic polymer may
further comprise a plurality of liquid crystal side-chains, where the liquid crystal
side-chains confer solubility to the telechelic polymer in the liquid crystal molecules,
or alternatively the telechelic polymer may be a main-chain polymer comprising a
plurality of liquid crystal mesogens, where the main-chain confers solubility to the
35 telechelic polymer in the liquid crystal molecules, or again alternatively the

1

telechelic polymer may comprise a mixed side-chain/main-chain polymer, where at least one of the main-chain or the side-chain confers solubility to the telechelic polymer in the liquid crystal molecules.

5

In such an embodiment the telechelic polymer may be cross-linked by any suitable means. For example, the telechelic polymer may further comprise at least two crosslinking groups at either end of the telechelic polymer.

10

In an alternative embodiment the crosslinking group is made crosslinkable with other crosslinking groups by application of either a photo or thermal initiating energy. In such an embodiment the photo initiating energy may be selected from any suitable source, such as, for example, UV-light, X-ray, gamma-ray, and radiation with high-energy electrons or ions.

15

In still yet another alternative embodiment, the liquid crystal molecules are aligned according to a geometry selected from the group consisting of: uniaxial, twisted, supertwisted, tilted, chevron and bookshelf.

20

In still another embodiment, the invention is directed to an electrooptic device incorporating the electro-optically active gel layer of the invention. Any suitable electrooptic device may be utilized, such as, for example, a liquid crystal display device or an electroluminescent lamp.

25

In still yet another embodiment, the invention is directed to a method for constructing an electrooptic device utilizing the electro-optically active gel layer of the invention. The method comprising homogeneously dispersing a small quantity of the high molecular weight polymer described above into a quantity of liquid crystal molecules, orienting the liquid crystal molecules and polymers and sparsely crosslinking the polymers to form an anisotropic polymer network adapted to mechanically stabilize the liquid crystal molecules. In such a method the anisotropic polymer network may also be adapted to dictate the alignment of the liquid crystal molecules.

30

BRIEF DESCRIPTION OF THE DRAWINGS

These and other features and advantages of the present invention will be better understood by reference to the following detailed description when considered in conjunction with the accompanying drawings wherein:

35

FIG. 1a is a schematic view of a system for aligning liquid crystal molecules according to the prior art.

1

FIG. 1b is a schematic view of a system for aligning liquid crystal molecules according to the prior art.

5

FIG. 1c is a schematic view of a system for aligning liquid crystal molecules according to the prior art.

FIG. 1d is a schematic view of a system for aligning liquid crystal molecules according to the present invention.

FIG. 2a is a schematic view of a polymer liquid crystal alignment system according to the present invention.

10

FIG. 2b is a schematic view of a polymer liquid crystal alignment system according to the present invention.

FIG. 2c is a schematic view of a polymer liquid crystal alignment system according to the present invention.

15

FIG. 3 is a synthesis pathway of an embodiment of the polymer according to the present invention.

FIG. 4 is a synthesis pathway of an embodiment of the polymer according to the present invention.

20

FIG. 5 is a synthesis pathway of an embodiment of the polymer according to the present invention.

FIG. 6 is a graphical representation of the liquid crystal properties of a liquid crystal system according to the present invention.

FIG. 7 is a graphical representation of the liquid crystal properties of a liquid crystal system according to the present invention.

25

FIG. 8 is a graphical representation of the liquid crystal properties of a liquid crystal system according to the present invention.

FIG. 9 is a schematic diagram of an electrooptical device incorporating the electroelectro-optically active liquid crystal material of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

30

The present invention is directed to an electro-optically active liquid crystal gel comprising a low concentration sparsely cross-linked homogeneously dispersed liquid crystal soluble polymer and a mixture of liquid crystal molecules.

35

As discussed above, there are a number of different methods for controlling the orientation of the liquid crystals. FIGs. 1a to 1c schematically show the conventional methods for inducing alignment control in liquid crystal electrooptical

1 devices. FIG. 1a shows the conventional rubbed polymer method of orienting both
nematic and ferroelectric displays 10. In this method, the liquid crystal
5 molecules 12 are disposed between surfaces 14 on each side of the device 10 and
aligned parallel to the surfaces 14 using rubbed polymer layers 16. There are a
number of difficulties associated with this approach, mainly associated with the
rubbing procedure that is needed to induce the orientation in the alignment
layers 16. In addition, mechanical stress can cause disruption of the liquid crystal
10 structure and in some displays, such as, for example, ferroelectric display's
alignment does not always recover after having been perturbed by mechanical
stress.

A second general method for aligning liquid crystals 12 is shown in FIGs. 1b
and 1c and uses polymer molecules 18 to control alignment and provide mechanical
15 stability, rather than a separate mechanical alignment layer. There are two
general techniques, polymer-stabilized liquid crystals, shown in FIG. 1b, and
polymer-dispersed liquid crystals, shown in FIG. 1c. In contrast to the use of
alignment layers, in which the interactions between the liquid crystal molecules 12
and the polymer 18 occur only at the interface 16 between the solid polymer layer
20 and the liquid crystal 12, the polymer-dispersed and polymer-stabilized techniques
provide intimate contact between the polymer molecules 18 and the liquid
crystal 12. In this technique, the alignment polymer 18 is typically made
anisotropic by either an alignment layer or by applying an electric field, then after
the desired orientation of the solvated polymer 18 is generated, the polymer 18 is
25 transformed so that it provides a lasting memory of the orientation state, e.g., by
photochemically or thermally-triggered polymerization of mesomers or cross linking
of oligomers or thermally triggered physical association. Although these techniques
do improve the mechanical stability of the liquid crystals 12, the current techniques
rely on high concentrations of polymer 18 to achieve cross-linking which can
30 significantly slow down switching times and efficiency. In addition, polymer-
dispersed liquid crystals can sometimes require high applied switching voltages and
display devices made using both of these techniques tend to be hazy.

The electro-optically active gel layer 20 in accordance with the present
invention is shown in FIG. 1d. The electro-optically active gel layer 20 comprises
35 a dilute solution of an anisotropic network 23 of polymer 24 solute homogeneously
dispersed within a solvent comprising a homogeneous or heterogeneous mixture of

1

5

10

small liquid crystal molecules **22**. The anisotropic network **23** of cross-linkable polymer **24** solute itself comprises a cross-linkable backbone **26** and a plurality of liquid crystal mesogens **28** attached thereto. The anisotropic network of polymer **24** is characterized in that an orientation can be induced into the polymer **24** via an external orienting influence and then frozen into an anisotropic network **23** of polymer molecules **24** via a physical or chemical cross-linking reaction between the individual polymers **24**. The unbound ferroelectric or nematic liquid crystal molecules **22** of the electro-optically active material **20** in solution with the polymer **24** solute are then subject to interactions with the oriented anisotropic network **23** of polymer **24** such that the orientation of the liquid crystal molecules **22** is dictated by the orientation of the anisotropic network of polymer **24**.

15

20

25

Any homogenous or heterogenous mixture of liquid crystal molecules **22** can be utilized as a solvent such that the electro-optically active layer **20** is in a gel state and exhibits nematic, chiral nematic, ferroelectric, antiferroelectric or electroclinic properties and such that during operation the liquid crystal molecules **22** exhibit a suitable electro-optically active phase under conventional operating conditions for an electrooptic device, such as, for example, a nematic, chiral nematic, smectic C chiral smectic C or smectic A phase at temperatures in the range from about -10° to 60°C. Because a variety of different electrooptic devices are contemplated, any suitable liquid crystal molecules or mixtures can be used, such as, for example, nematic cyanobiphenyl (CB) based liquid crystals or eutectic mixtures thereof, or ferroelectric phenylbenzoate (PB) based liquid crystals, Zli 3654 (Merck) or eutectic mixtures thereof or various fluorinated liquid crystals or eutectic liquid crystal mixtures. In another embodiment, liquid crystal molecules **22** having dichroic properties are utilized such that a polarizer is not required in any electrooptical device utilizing the electro-optically active material **20** of the invention.

30

35

The polymer **24** solute is chosen such that it is soluble in the liquid crystal molecules **22** solvent and can be sparsely cross-linked even under dilute conditions to form an oriented anisotropic three-dimensional polymer network **23** which is a liquid crystal gel electro-optically active material **20**. Although any suitably dilute concentration of polymer **24** may be utilized such that the switching speed of the liquid crystal is not significantly reduced (for example, where the switching time more than doubles over the switching time of the pure liquid crystal molecules **22**)

and such that the polymer molecules **24** are capable of sparsely cross-linking to form the polymer network, in one preferred embodiment the electro-optically active layer comprises less than 5% of the gel layer by mass and more preferably equal to or less than 2% of the gel layer by mass.

In light of the functional requirements, high molecular weight polymer molecules **24**, such as, for example, polymers with a molecular weight of at least 100,000 g/mol, more preferably at least 500,000 g/mol, and even more preferably polymers with a molecular weight of at least 1 million g/mol, having side-unit or main-chain liquid crystal groups or mesogens **28** with an affinity for the liquid crystal molecules **22** of the electro-optically active material **20** and having only a few insoluble and/or cross-linking blocks or functional groups **30** are chosen. Within the structural features listed above, however, any polymer **24** that can coordinate or bond with the chosen liquid crystal and which provides sufficient field-off anisotropy and/or suitable structural stability can be utilized in the current invention, such as, for example, block or telechelic polymers. Furthermore, the polymer **24** can be made using any suitable technique, such as, for example, radical, anionic, or polymer analogous, in which the polymer backbone **26** is first made, then a mesogen **28** added, and then the polymers are cross-linked via a cross-linkable end portion **30**. The liquid crystal mesogen **28** can be linked to the polymer via any suitable means, such as, for example, by incorporation of the mesogen **28** into the main-chain of the polymer or attachment of the mesogen **28** as a side-unit, with or without a spacer **31**. Likewise, although only end cross-linking or insoluble groups **30** are shown, it should be understood that such groups **30** may be positioned at any point along the chain of the polymer **24**.

FIGs. 2a to 2c schematically depict three possible polymers **24** according to the present invention. FIG. 2a depicts the reaction between a polymer backbone **26** and a liquid crystal mesogen **28** in which the liquid crystal **28** is attached as a side-unit to the backbone **26** to form a side-chain polymer **24** according to the present invention. FIG. 2b shows the reaction between a plurality of liquid crystal mesogens **28** in to form a main-chain polymer **24** according to the present invention. Finally, FIG. 2c depicts the formation of a block or telechelic polymer having end-units **30** attached to either end of the backbone **26** to provide a cross-linking function to the polymer **24** according to the present invention.

1
Although the embodiments of the polymer **24** shown in FIGs. 2a to 2c all depict either main-chain or side-chain block polymers, it should be understood that any polymer **24** with the suitable alignment, structural and solubility characteristics could be utilized in the electro-optically active gel layer **20** according to the present invention. In addition, any suitable method of cross-linking the individual polymer molecules **24** to form the polymer network **23** of the electro-optically active material **20** can be utilized. For example, in the embodiment of the invention shown in FIG. 2c, the anisotropic network **23** is created by self-assembly of a block copolymer **24** comprising end blocks **30** that are insoluble in the liquid crystal molecules **22** such that they aggregate to form the physical cross-links and midblocks or backbones **26** that are soluble in the liquid crystal molecules **22**. In another embodiment, the polymer network **23** of the current invention is formed by photo or thermally polymerizing the end blocks **30** of a prepolymer or macromer **24** that is soluble in the desired liquid crystal molecules **22**. Any suitable photo or thermal polymerizable end block **30** may be used, such as, for example, acrylates, methacrylates, epoxy compounds and/or thiolene systems. In the case of photopolymerization, an additional photo-initiator may be required, such as, for example, Igacure 651 (Merck). Any suitable radiation may be used to trigger the photopolymerization, such as, for example, UV-light, X-rays, gamma-rays or radiation with high-energy particles such as electrons and ions

In either such embodiment the solubility of the midblock or backbone **26** of the polymer **24** is conferred either by soluble units within the main-chain (as shown schematically in FIG. 2b), by side-groups selected to confer solubility (as shown in FIG. 2a), or by a mixture of the two techniques. Any suitable solubilizing units or mesogens **28** can be utilized, such as, for example, any homogenous or heterogenous mixture of liquid crystal molecules exhibiting nematic, ferroelectric, antiferroelectric or electroclinic properties and such that the mesogens **28** have an affinity for the liquid crystal molecules **22** of the electro-optically active material **20**. Such mesogens **28** may exhibit any suitable electro-optically active phase, such as, for example, a nematic, chiral nematic, chiral smectic C, smectic C or smectic A phase. Because a variety of different electrooptic devices are contemplated, any suitable liquid crystal molecules or mixtures can be used, such as, for example, nematic cyanobiphenyl (CB) based liquid crystals or eutectic mixtures thereof, or ferroelectric phenylbenzoate (PB) based liquid crystals, Zli 3654 (Merck) or eutectic

1 mixtures thereof, or of various fluorinated liquid crystals or eutectic mixtures
thereof. In another embodiment, mesogens **28** having dichroic properties are
utilized such that a polarizer is not required in any electrooptical device utilizing
5 the electro-optically active material **20** of the invention.

Orientation can be induced in the liquid crystal molecules **22** by any suitable
technique. For example, uniaxial, twisted, supertwisted, tilted, chevron and
bookshelf orientations of the liquid crystal molecules **22** can be induced in the
electro-optically active material **20** of the current invention by varying the
10 orientation directions of orientation layers and the thickness of the cell holding the
electro-optically active material **20** as shown in FIG. 1a and then fixing the
orientation by cross-linking the polymers **24** of the electro-optically active material
20 to form an oriented polymer network **23** as described above. Although
orientation layers do provide one method of providing an initial orientation to the
15 electro-optically active material **20** of the current invention, it should be understood
that orientation layers are not needed to maintain orientation of the liquid crystal
molecules **22**, as in many conventional electro-optically active materials, since such
orientation is provided by the polymer network **23** itself. In one embodiment, then,
a desired orientation is first provided by an external field or flow, such as, for
20 example, an electrical or magnetic field, or an oscillatory or unidirectional shear
induced flow, or an extensional stress and then the induced orientation is fixed via
cross-linking of the polymer molecules **24** and formation of the anisotropic polymer
network **23**.

The invention is also directed to a method of forming the electro-optically
25 active liquid crystal gel according to the invention. Accordingly, in one exemplary
embodiment, an electro-optically active material **20** of the current invention was
formed utilizing a polymer analogous approach. The electro-optically active gel
solution **20** was formed by mixing cyanobiphenyl liquid crystal molecules **22**, with
a cyanobiphenyl polymer **24** synthesized according to the reaction scheme in FIG.
30 3. The cyanobiphenyl or CB based liquid crystal molecules **22** can be synthesized
according to conventional techniques or alternatively purchased either as a purified
substance, such as, for example, CB5 or CB50 (Merck) or as a mixture of liquid
crystal molecules, such as, for example E7 or E44 (Merck). In this mixture the
backbone **26** of the polymer **24** is a 1,2-polybutadiene polymer **24**, synthesized
35 according to the reaction scheme in FIG. 4. Alternatively, the polymer may be

synthesized according to the reaction scheme shown in FIG. 5. To encourage cross-linking of the polymer molecules, conventional end blocks or end functional groups **30** are added to the mixture. These groups may provide either physical or chemical cross-linking under a variety of conditions. To prevent aggregation, or cross-linking before an orientation has been induced in the gel, the mixture is brought to a high temperature at which aggregation does not occur. Although this temperature may vary according to the cross-linking group utilized, typically a temperature of about 80°C ensures that the polymer molecules can still flow. At this temperature the mixture is usually in the nematic phase, and can be oriented under the influence of a conventional alignment layer, an external electric field, or a shear strain. Under said conditions an anisotropic orientation of the electro-optically active material **20** is obtained. Subsequently, the polymer **24** is made to cross-link or aggregate to form an anisotropic network and an electro-optically active layer either by simply cooling temperature of mixture to a point at which self-assembly of the cross-linkable units **30** aggregate or cross-link, typically about 30°C, or via photo or thermal initiate cross-linking. Although the above method utilizes a polymer analogous approach to synthesize the polymer **24** according to the invention, it should be understood that any suitable method may be used, such as, for example, by radical or anion techniques. Likewise, although a block copolymer is described any suitable polymer may be synthesized, such as, for example a telechelic polymer.

Because dilute solutions of high molecular weight polymers have never been used to make electro-optically active materials, FIGs. 6 to 8 show a series of experiments taken using solutions of the high molecular weight polymers according to the invention. FIG. 6 shows that the addition of a low concentration of a high molecular weight polymer according to the present invention can yield high rheological control of liquid crystal alignment. In this case a solution of only 10% polymer having a molecular weight of 800,000 g/mol in a solution of liquid crystal molecules causes the liquid crystal molecules to become flow-aligning not merely parallel to the velocity direction as in solutions containing similar concentrations of small molecular weight polymers, but to become flow-aligning parallel to the velocity gradient direction. Such flow-aligning characteristics indicate that low concentrations of the high molecular weight polymers of the current invention can yield electro-optically active materials having excellent rheological control

properties previously only obtainable using high concentrations of low molecular weight polymers.

FIG. 7 shows that the polymer solutions according to the invention can be obtained with a variety of pure liquid crystals and liquid crystal mixtures, such as, for example 50 CB and 5 CB (Merck) as well as in several eutectic mixtures of liquid crystal molecules, such as, for example E7 and E44 (Merck). While these cyanobiphenyl and eutectic mixtures have been utilized in the current embodiments, it should be understood that such optical properties can also be obtained with a variety of other liquid crystal molecules and eutectic mixtures thereof.

The electro-optically active gel material **20** of the current invention is characterized in that the solution of liquid crystal molecules **22** solvent to polymer **24** solute is a dilute solution such that the switching speed of the electro-optically active material **20** remains fast. FIG. 8 shows a graph of switching time versus the percent polymer **24**, as described above having a molecular weight of $\sim 800,000$ g/mol, in the liquid crystal solution. Typical electrooptical devices, such as, for example, liquid crystal display devices have switching times of about 10 ms. Typically, polymer aligning agents are only useful if the switching time of the liquid crystal with the aligning agent is less than double the switching time of the pure liquid crystal material. As shown in FIG. 8, the pure liquid crystal material used in the embodiment shown has a switching time of ~ 14.6 ms/ μm^2 and any increase in the quantity of the polymer **24** leads to a substantial increase in the switching time of the device. In the present case, then, the quantity of polymer **24** is held at about 2% or less, as calculated by weight percent of the polymer to solution such that the switching time of the electrooptical device remains less than double the pure liquid crystal switching time. However, this concentration is measured for nematic displays, which are significantly slower than ferroelectric displays. As such, it should be understood that the concentration of polymer in ferroelectric displays could be significantly increased given the inherent switching time of such devices. For example, in the present case, concentrations as high as 6% could be used.

FIG. 9 diagrammatically shows a cross-sectional view of an electrooptic device capable of utilizing the electro-optically active material in accordance with the invention, when configured as a display device **32**. The display device **32**

1 comprises two glass substrates 34 and 36 which are provided with a matrix of transparent electrode layers 38 and 40 on the sides facing each other. The electrode layers 38 and 40 can be individually drive via electrically conductive tracks (not shown). On the matrix of the electrode layers 38 and 40 there are provided an orientation layer 42 and 44 of rubbed polyimide. The distance 46 between both orientation layers 42 and 44 forms the thickness of the electro-optically active layer 48 described above. By orienting and then fixing the electro-optically active layer 48 as described above, an oriented electro-optically active layer 48 can be obtained. Although a passive matrix display 32 is described herein, it should be understood that any electrooptic device could be manufactured utilizing the electro-optically active material of the present invention, such as, for example, an active matrix display.

15 The elements of the apparatus and the general features of the components are shown and described in relatively simplified and generally symbolic manner. Appropriate structural details and parameters for actual operation are available and known to those skilled in the art with respect to the conventional aspects of the process.

20 Although specific embodiments are disclosed herein, it is expected that persons skilled in the art can and will design alternative electro-optically active materials and electrooptic devices that are within the scope of the following claims either literally or under the Doctrine of Equivalents.